

## TECHNICAL PLASTIC AND METAL PARTS

Drive fastener 137

| Code            | Description | Price euro/1000 | % Price ( | Change<br>2 | Package | Α   | В | С   | D  | Ε   | F  | gr |
|-----------------|-------------|-----------------|-----------|-------------|---------|-----|---|-----|----|-----|----|----|
| 137 0030 000 05 | MP 137-03   | 113,00          | + 60%     | -           | 500     | 4.7 | 1 | 5.5 | 10 | 1.7 | 15 |    |

 Colour transparent - natural
 Colour description
 transparent - natural

 Matches
 Natural matches Milk-like; transparent white colour can differ per kind of material.

 Featured colours reserved. Due to the screen, differences in colour may occur.

MaterialMaterial nrPolyoxymethylene (POM) POM05 (XXX XXXX XXX)

## **General informations:**

Strong durable material, suitable for flexible connection elements and numerous other technical products. Resembles nylon, yet the taking in of moisture is less than 0,5%, so a higher dimensional stability is reached and is very well insulating electrically. Suitable for suspending clamps, bearings, gear-wheels etc. POM can be glued.

| Features                                   |                     | Chimical resistance |            |  |  |
|--|---------------------|---------------------|------------|--|--|
| feature                                    | DIN                 | Resistance to       | Valutation |  |  |
| Relative density gr/cm <sup>3</sup>        | 1,42                | Petrol              | Α          |  |  |
| Tensile strength MN/m <sup>2</sup>         | 75                  | Benzene             | Α          |  |  |
| Elongation at break %                      | 65                  | Mineral oils        | Α          |  |  |
| Tensile modulus MN/m <sup>2</sup>          | 3000                | Vegetable oils      | Α          |  |  |
| Notched impact strength kJ/m <sup>2</sup>  | 8.5                 | Weak alkalis        | Α          |  |  |
| Ball indentation MN/m <sup>2</sup>         | 140<br>100<br>10^15 | Strong alkalis      | В          |  |  |
| Application temperature max °C             |                     | Weak acids          | -<br>C     |  |  |
| Volume resistivity cm                      |                     | Strong acids        |            |  |  |
| Dissapation factor tan. 10 <sup>3</sup> Hz | 0,025               | A = good            |            |  |  |
| Dielectric strength MV/m                   | 70                  | <b>B</b> = doubtful |            |  |  |
| Flammability UL94 > 1,6 mm                 | HB                  | <b>C</b> = poor     |            |  |  |
| Coefficient of friction (on steel)         | 0,25                |                     |            |  |  |
| All data are indicative                    |                     |                     |            |  |  |

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

**GANDINI FASTENERS SRL** viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts
machining

GANDINI PASTENERS SRE viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

**GANDINI FASTENERS SRL** Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350