

TECHNICAL PLASTIC AND METAL PARTS

										ar w 104	heel I	
	Code	Description	Price euro/1000	% Price Change 1 2	Package	A	В	С	D	Е	F	gr
10	4 0014 000 05	MP 104-14	16.653,00	+ 60% -	1	1	60	8	16	8	20	

Colour	Colour number	r					
transparent - natural	000 (XXX XX	000 (XXX XXX XXX XX)					
Colour descriptiontransparentMatchesNatural maiFeatured colours reserved. Due to the	tches Milk-like; transpa	rent white colour can differ per kind n colour may occur.	l of material.				
Material		Material nr					
Polyoxymethylene (POM) POM		05 (XXX XXXX XXX XX)					
General informations: Strong durable material, suitable for yet the taking in of moisture is less t electrically. Suitable for suspending	han 0,5%, so a higher	dimensional stability is reached and					
Features		Chimical resistance					
feature	DIN	Resistance to	Valutation				
Relative density gr/cm ³	1,42	Petrol	А				
Tensile strength MN/m ²	75	Benzene	А				
Elongation at break %	65	Mineral oils	А				
Tensile modulus MN/m ²	3000	Vegetable oils	А				
Notched impact strength kJ/m ²	8.5	Weak alkalis	A				
Ball indentation MN/m ²	140	Strong alkalis	В				
Application temperature max °C	100	Weak acids	-				
Volume resistivity cm	10^15	Strong acids	С				
Dissapation factor tan. 10 ³ Hz	0,025	A = good					
Dielectric strength MV/m	70	B = doubtful					
Flammability UL94 > 1,6 mm	HB	C = poor					
Coefficient of friction (on steel)	0,25						

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350