

# TECHNICAL PLASTIC AND METAL PARTS



Code	Description	Price euro/1000	% Price Change 1	% Price Change 2	Package	A	B	C	D	E	F	gr
167 0027 000 02	MP 167-27	216,00	+ 60%	-	100	3.0	18.5	5.4	D1	4	16.5	

Colour	Colour number
transparent - natural	000 (XXX XXXX XXX XX)
<b>Colour description</b>	transparent - natural
<b>Matches</b>	Natural matches Milk-like; transparent white colour can differ per kind of material.
Featured colours reserved. Due to the screen, differences in colour may occur.	

Material	Material nr																																																								
Nylon - 66 PA - 66	02 (XXX XXXX XXX XX)																																																								
<b>General informations:</b> A strong, tough and durable material. Suitable for connecting elements and other technical components. Owing to selflubricant properties ideal for slide bearings. Takes in approx 2 % moisture (a little less than nylon-6) and is then at its strongest. Therefore always has to acclimatize for a few days after injection moulding. Operational temperature up to 120°C. Nylon is self extinguishing.																																																									
<table><tr><th colspan="2">Features</th><th colspan="2">Chemical resistance</th></tr><tr><th>feature</th><th>DIN</th><th>Resistance to</th><th>Valutation</th></tr><tr><td>Relative density gr/cm<sup>3</sup></td><td>1,14</td><td>Petrol</td><td>A</td></tr><tr><td>Tensile strength MN/m<sup>2</sup></td><td>60</td><td>Benzene</td><td>A</td></tr><tr><td>Elongation at break %</td><td>140</td><td>Mineral oils</td><td>A</td></tr><tr><td>Tensile modulus MN/m<sup>2</sup></td><td>1500</td><td>Vegetable oils</td><td>A</td></tr><tr><td>Notched impact strength kJ/m<sup>2</sup></td><td>17</td><td>Weak alkalis</td><td>A</td></tr><tr><td>Ball indentation MN/m<sup>2</sup></td><td>100</td><td>Strong alkalis</td><td>B</td></tr><tr><td>Application temperature max °C</td><td>120</td><td>Weak acids</td><td>B</td></tr><tr><td>Volume resistivity cm</td><td>10<sup>15</sup></td><td>Strong acids</td><td>C</td></tr><tr><td>Dissapation factor tan. 10<sup>3</sup> Hz</td><td>0,15</td><td colspan="2"><b>A = good</b></td></tr><tr><td>Dielectric strength MV/m</td><td>30</td><td colspan="2"><b>B = doubtful</b></td></tr><tr><td>Flammability UL94 &gt; 1,6 mm</td><td>V2</td><td colspan="2"><b>C = poor</b></td></tr><tr><td>Coefficient of friction (on steel)</td><td>0,3</td><td colspan="2"></td></tr></table>		Features		Chemical resistance		feature	DIN	Resistance to	Valutation	Relative density gr/cm <sup>3</sup>	1,14	Petrol	A	Tensile strength MN/m <sup>2</sup>	60	Benzene	A	Elongation at break %	140	Mineral oils	A	Tensile modulus MN/m <sup>2</sup>	1500	Vegetable oils	A	Notched impact strength kJ/m <sup>2</sup>	17	Weak alkalis	A	Ball indentation MN/m <sup>2</sup>	100	Strong alkalis	B	Application temperature max °C	120	Weak acids	B	Volume resistivity cm	10 <sup>15</sup>	Strong acids	C	Dissapation factor tan. 10 <sup>3</sup> Hz	0,15	<b>A = good</b>		Dielectric strength MV/m	30	<b>B = doubtful</b>		Flammability UL94 > 1,6 mm	V2	<b>C = poor</b>		Coefficient of friction (on steel)	0,3		
Features		Chemical resistance																																																							
feature	DIN	Resistance to	Valutation																																																						
Relative density gr/cm <sup>3</sup>	1,14	Petrol	A																																																						
Tensile strength MN/m <sup>2</sup>	60	Benzene	A																																																						
Elongation at break %	140	Mineral oils	A																																																						
Tensile modulus MN/m <sup>2</sup>	1500	Vegetable oils	A																																																						
Notched impact strength kJ/m <sup>2</sup>	17	Weak alkalis	A																																																						
Ball indentation MN/m <sup>2</sup>	100	Strong alkalis	B																																																						
Application temperature max °C	120	Weak acids	B																																																						
Volume resistivity cm	10 <sup>15</sup>	Strong acids	C																																																						
Dissapation factor tan. 10 <sup>3</sup> Hz	0,15	<b>A = good</b>																																																							
Dielectric strength MV/m	30	<b>B = doubtful</b>																																																							
Flammability UL94 > 1,6 mm	V2	<b>C = poor</b>																																																							
Coefficient of friction (on steel)	0,3																																																								
<b>All data are indicative</b>																																																									

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.l. All rights reserved. No part of this web site may be reproduced in any form without express permission.

**GANDINI FASTENERS SRL** viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy  
Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution  
of fasteners, fixing elements  
and mechanical parts  
machining

**GANDINI FASTENERS SRL**  
viale Pier Paolo Pasolini, 83  
Sesto San Giovanni Mi - Italy

**Sales department**  
250@gandini.it  
tel +39 02 241 047 250

**Administration**  
350@gandini.it  
tel +39 02 241 047 350