

TECHNICAL PLASTIC AND METAL PARTS



Code	Description	Price euro/1000	% Price Change	Package	A	B	C	D	E	F	gr
167 0035 699 02	MP 167-35 NERO	288,00	+ 60%	100	4.8	11.1	11	D1	0.9	5.3	

Colour	Colour number
black	699 (XXX XXXX XXX XX)
Colour description	black
Matches	brilliant black. Matches: Reasonably matches RAL colour 9005
Featured colours reserved. Due to the screen, differences in colour may occur.	

Material	Material nr																																																								
Nylon - 66 PA - 66	02 (XXX XXXX XXX XX)																																																								
General informations: A strong, tough and durable material. Suitable for connecting elements and other technical components. Owing to selflubricant properties ideal for slide bearings. Takes in approx 2 % moisture (a little less than nylon-6) and is then at its strongest. Therefore always has to acclimatize for a few days after injection moulding. Operational temperature up to 120°C. Nylon is self extinguishing.																																																									
<table><tr><th colspan="2">Features</th><th colspan="2">Chemical resistance</th></tr><tr><th>feature</th><th>DIN</th><th>Resistance to</th><th>Valutation</th></tr><tr><td>Relative density gr/cm³</td><td>1,14</td><td>Petrol</td><td>A</td></tr><tr><td>Tensile strength MN/m²</td><td>60</td><td>Benzene</td><td>A</td></tr><tr><td>Elongation at break %</td><td>140</td><td>Mineral oils</td><td>A</td></tr><tr><td>Tensile modulus MN/m²</td><td>1500</td><td>Vegetable oils</td><td>A</td></tr><tr><td>Notched impact strength kJ/m²</td><td>17</td><td>Weak alkalis</td><td>A</td></tr><tr><td>Ball indentation MN/m²</td><td>100</td><td>Strong alkalis</td><td>B</td></tr><tr><td>Application temperature max °C</td><td>120</td><td>Weak acids</td><td>B</td></tr><tr><td>Volume resistivity cm</td><td>10¹⁵</td><td>Strong acids</td><td>C</td></tr><tr><td>Dissipation factor tan. 10³ Hz</td><td>0,15</td><td colspan="2">A = good</td></tr><tr><td>Dielectric strength MV/m</td><td>30</td><td colspan="2">B = doubtful</td></tr><tr><td>Flammability UL94 > 1,6 mm</td><td>V2</td><td colspan="2">C = poor</td></tr><tr><td>Coefficient of friction (on steel)</td><td>0,3</td><td colspan="2"></td></tr></table>		Features		Chemical resistance		feature	DIN	Resistance to	Valutation	Relative density gr/cm ³	1,14	Petrol	A	Tensile strength MN/m ²	60	Benzene	A	Elongation at break %	140	Mineral oils	A	Tensile modulus MN/m ²	1500	Vegetable oils	A	Notched impact strength kJ/m ²	17	Weak alkalis	A	Ball indentation MN/m ²	100	Strong alkalis	B	Application temperature max °C	120	Weak acids	B	Volume resistivity cm	10 ¹⁵	Strong acids	C	Dissipation factor tan. 10 ³ Hz	0,15	A = good		Dielectric strength MV/m	30	B = doubtful		Flammability UL94 > 1,6 mm	V2	C = poor		Coefficient of friction (on steel)	0,3		
Features		Chemical resistance																																																							
feature	DIN	Resistance to	Valutation																																																						
Relative density gr/cm ³	1,14	Petrol	A																																																						
Tensile strength MN/m ²	60	Benzene	A																																																						
Elongation at break %	140	Mineral oils	A																																																						
Tensile modulus MN/m ²	1500	Vegetable oils	A																																																						
Notched impact strength kJ/m ²	17	Weak alkalis	A																																																						
Ball indentation MN/m ²	100	Strong alkalis	B																																																						
Application temperature max °C	120	Weak acids	B																																																						
Volume resistivity cm	10 ¹⁵	Strong acids	C																																																						
Dissipation factor tan. 10 ³ Hz	0,15	A = good																																																							
Dielectric strength MV/m	30	B = doubtful																																																							
Flammability UL94 > 1,6 mm	V2	C = poor																																																							
Coefficient of friction (on steel)	0,3																																																								
All data are indicative																																																									

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.l. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy
Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution
of fasteners, fixing elements
and mechanical parts
machining

GANDINI FASTENERS SRL
viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

Sales department
250@gandini.it
tel +39 02 241 047 250

Administration
350@gandini.it
tel +39 02 241 047 350