


TECHNICAL PLASTIC AND METAL PARTS



| Code | Description | Price euro/1000 | % Price Change | Package | A | B | C | D | E | F | gr |
|-----------------|------------------|-----------------|----------------|---------|-----|-----------|------------|------|------|-----|----|
| 167 2065 699 02 | MP 167-2065 NERO | 198,00 | + 60% | - | 100 | 5.6 - 6.4 | 1.5 - 15.0 | 13.0 | 20.0 | 1.5 | 1 |

| Colour | Colour number |
|--|--|
| black | 699 (XXX XXXX XXX XX) |
| Colour description | black |
| Matches | brilliant black. Matches: Reasonably matches RAL colour 9005 |
| Featured colours reserved. Due to the screen, differences in colour may occur. | |

| Material | Material nr |
|---|----------------------|
| Nylon - 66 PA - 66 | 02 (XXX XXXX XXX XX) |
| General informations: A strong, tough and durable material. Suitable for connecting elements and other technical components. Owing to selflubricant properties ideal for slide bearings. Takes in approx 2 % moisture (a little less than nylon-6) and is then at its strongest. Therefore always has to acclimatize for a few days after injection moulding. Operational temperature up to 120°C. Nylon is self extinguishing. | |
| Features | |
| feature | DIN |
| Relative density gr/cm ³ | 1,14 |
| Tensile strength MN/m ² | 60 |
| Elongation at break % | 140 |
| Tensile modulus MN/m ² | 1500 |
| Notched impact strength kJ/m ² | 17 |
| Ball indentation MN/m ² | 100 |
| Application temperature max °C | 120 |
| Volume resistivity cm | 10^15 |
| Dissapation factor tan. 10 ³ Hz | 0,15 |
| Dielectric strength MV/m | 30 |
| Flammability UL94 > 1,6 mm | V2 |
| Coefficient of friction (on steel) | 0,3 |
| All data are indicative | |
| Chemical resistance | |
| Resistance to | Valutation |
| Petrol | A |
| Benzene | A |
| Mineral oils | A |
| Vegetable oils | A |
| Weak alkalis | A |
| Strong alkalis | B |
| Weak acids | B |
| Strong acids | C |
| A = good B = doubtful C = poor | |

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.l. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S. Giovanni Milano Italy
Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution
of fasteners, fixing elements
and mechanical parts
machining

GANDINI FASTENERS SRL
viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

Sales department
250@gandini.it
tel +39 02 241 047 250

Administration
350@gandini.it
tel +39 02 241 047 350