

TECHNICAL PLASTIC AND METAL PARTS

					Furniture ferrule 009
Code	Description	Price euro/1000	% Price Change 1 2	Package A	B C DE F gr
009 0040 220 03	MP 09- 4 NERO	115,00	+ 60% -	100 4	11 F1

Colour		r						
black	220 (XXX XXXX XXX XX)							
Colour descriptionblaMatchesblaFeatured colours reserved. Due to the	ck. Matches : Rough	ly matches RAL colour 9004 in colour may occur.						
aterial Material nr								
polyethylene Ld - PE		03 (XXX XXXX XXX XX)						
General informations: Low pressure polyethylene is resistant to most chemicals. Therefore especially suitable for coverplugs and caps. Because of great flexibility it is almost unbreakable. Does not take in moisture. Therefore insulating very well electrically. Polyethylene can not be glued and burns on after lighting it. Features Chimical resistance								
feature	DIN	Resistance to	Valutation					
Relative density gr/cm ³	0.92	Petrol	А					
Tensile strength MN/m ²	10	Benzene	А					
Elongation at break %	300	Mineral oils	А					
Tensile modulus MN/m ²	180	Vegetable oils	А					
Notched impact strength kJ/m ²	-	Weak alkalis	А					
Ball indentation MN/m ²	14	Strong alkalis	А					
Application temperature max °C	70	Weak acids	А					
Volume resistivity cm	10^17	Strong acids	В					
Dissapation factor tan. 10 ³ Hz	0,0003	A = good						
Dielectric strength MV/m	60	B = doubtful						
Flammability UL94 > 1,6 mm	-	C = poor						
Coefficient of friction (on steel)	0,17-1,5							
All data are indicative								

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350