

**TECHNICAL PLASTIC AND METAL PARTS** 

						ure ferrule 009
Code	Description	Price euro/1000	% Price Change 1 2	Package	ABC	DEF gr
009 0250 220 03	MP 09- 25 NERO	300,00	+ 60% -	50 2	5 24	F1

Colour	Colour numbe	er					
black	ck 220 (XXX XXX XXX XXX)						
Colour descriptionblacMatchesblacFeatured colours reserved. Due to the	ck. Matches : Rough	ly matches RAL colour 9004 in colour may occur.					
Material	aterial Material nr						
polyethylene Ld - PE		03 (XXX XXXX XXX <b>XX</b> )					
Low pressure polyethylene is resistant great flexibility it is almost unbreakable can not be glued and burns on after lig Features	. Does not take in m						
feature	DIN	Resistance to	Valutation				
Relative density gr/cm <sup>3</sup>	0,92	Petrol	А				
Tensile strength MN/m <sup>2</sup>	10	Benzene	А				
Elongation at break %	300	Mineral oils	А				
Tensile modulus MN/m <sup>2</sup>	180	Vegetable oils	А				
Notched impact strength kJ/m <sup>2</sup>	-	Weak alkalis	А				
Ball indentation MN/m <sup>2</sup>	14	Strong alkalis	А				
Application temperature max °C	70	Weak acids	А				
Volume resistivity cm	10^17	Strong acids	В				
Dissapation factor tan. 10 <sup>3</sup> Hz	0,0003	A = good					
Dielectric strength MV/m	60	B = doubtful					
Flammability UL94 > 1,6 mm	-	<b>C</b> = poor					
Coefficient of friction (on steel)	0,17-1,5						
All data are indicative							

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

**GANDINI FASTENERS SRL** Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350