

**TECHNICAL PLASTIC AND METAL PARTS** 

								er cap <b>)6-k2</b>
Code	Description	Price euro/1000	% Price Cl 1	hange 2	Package	А	В	CDEFgr
006 2062 076 01	MP 06- 2- 6 CAPP.MARRONE	86,00	+ 60%	-	500	14.8	16.6	9

Colour	Colour num	ber							
brown	own 076 (XXX XXXX XXX XXX XX)								
Colour descriptionbroMatchesbroFeatured colours reserved. Due to the	wn. Matches: Roug	hly matches RAL colour 8019 es in colour may occur.							
Material		Material nr							
Nylon - 6 PA - 6		01 (XXX XXXX XXX <b>XX</b> )							
General informations: A strong, tough and durable material. lubricant properties ideal for slide bea Always has to acclimatize for a few d Features	arings. Takes in app	prox 3% moisture at room temperatu	ire and is then at its strongest.						
feature	DIN	Resistance to	Valutation						
Relative density gr/cm <sup>3</sup>	1,14	Petrol	А						
Tensile strength MN/m <sup>2</sup>	55	Benzene	А						
Elongation at break %	250	Mineral oils	А						
Tensile modulus MN/m <sup>2</sup>	950	Vegetable oils	А						
Notched impact strength kJ/m <sup>2</sup>	35	Weak alkalis	A						
Ball indentation MN/m <sup>2</sup>	82	Strong alkalis	В						
Application temperature max °C	120	Weak acids	В						
Volume resistivity cm	10^15	Strong acids	С						
Dissapation factor tan. 10 <sup>3</sup> Hz	0,2	A = good							
Dielectric strength MV/m	35	<b>B</b> = doubtful							
Flammability UL94 > 1,6 mm	V2	<b>C</b> = poor							
<b>,</b> - , -									
Coefficient of friction (on steel)	0,3								

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

**GANDINI FASTENERS SRL** Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350