

**TECHNICAL PLASTIC AND METAL PARTS** 

						Dri	ve fa: <b>09</b>		۶r
Code	Description	Price euro/1000	% Price Change 1 2	Package	A B	C D	E	F	gr
091 0006 599 02	MP 91-06 NERO	118,00	+ 60% -	500	0.8 4 4	.8 9.5	11	1.5	

Colour	Colour num	ber					
black	599 (XXX XXXX <b>XXX</b> XX)						
Colour descriptionblackMatchesjet blackFeatured colours reserved. Due to th	ack. Matches: Reas	sonably matches RAL colour 9005 es in colour may occur.					
Material Nylon - 66 PA - 66		Material nr 02 (XXX XXXX XXX <b>XX</b> )					
General informations: A strong, tough and durable material. selflubricant properties ideal for slide strongst. Therefore always has to acc Nylon is self extinguishing. Features	bearings. Takes in	approx 2 % moisture (a little less th	an nylon-6) and is then at its				
feature	DIN	Resistance to	Valutation				
Relative density gr/cm <sup>3</sup> Tensile strength MN/m <sup>2</sup>	1,14 60	Petrol Benzene	A				
Elongation at break %	140	Mineral oils	A				
Tensile modulus MN/m <sup>2</sup>	140	Vegetable oils	A				
Notched impact strength kJ/m <sup>2</sup>	17	Weak alkalis	A				
Ball indentation MN/m <sup>2</sup>	100	Strong alkalis	В				
Application temperature max °C	120	Weak acids	B				
Volume resistivity cm	10^15	Strong acids	С				
Dissapation factor tan. 10 <sup>3</sup> Hz	0,15	A = good					
Dielectric strength MV/m	30	<b>B</b> = doubtful					
Flammability UL94 > 1,6 mm	V2	<b>C</b> = poor					
	• =						
Coefficient of friction (on steel)	0,3						

Technical informations are indicative and can be updated. Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

**GANDINI FASTENERS SRL** Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350