

**TECHNICAL PLASTIC AND METAL PARTS** 

|      |             |                 |                |             |         |     |   |   | Dri  | ve fa<br><b>09</b> | stene<br>1 | r  |
|------|-------------|-----------------|----------------|-------------|---------|-----|---|---|------|--------------------|------------|----|
| Code | Description | Price euro/1000 | % Price (<br>1 | Change<br>2 | Package | A   | В | С | D    | Е                  | F          | gr |
|      |             |                 |                |             |         | 0.9 |   |   | 10.3 |                    |            |    |

| Colour   | lour Colour number   |   |                                |  |  |  |  |  |
|--|----------------------|---|--------------------------------|--|--|--|--|--|
| transparent - natural 000 (XXX XXXX XXX XXX)   |                      |   |                                |  |  |  |  |  |
| Colour descriptiontransparent -MatchesNatural matchesFeatured colours reserved. Due to the   | hes Milk-like; trans | parent white colour can differ per ki<br>s in colour may occur. | nd of material.                |  |  |  |  |  |
| Material   |                      | Material nr   |                                |  |  |  |  |  |
| Nylon - 66 PA - 66   |                      | 02 (XXX XXXX XXX <b>XX</b> )                                    |                                |  |  |  |  |  |
| <b>General informations:</b><br>A strong, tough and durable material.<br>selflubricant properties ideal for slide I<br>strongst. Therefore always has to acc<br>Nylon is self extinguishing. | pearings. Takes in   | approx 2 % moisture (a little less th                           | an nylon-6) and is then at its |  |  |  |  |  |
| Features   |                      | Chimical resistance   |                                |  |  |  |  |  |
| feature  | DIN                  | Resistance to   | Valutation                     |  |  |  |  |  |
| Relative density gr/cm <sup>3</sup>  | 1,14                 | Petrol  | А                              |  |  |  |  |  |
| Tensile strength MN/m <sup>2</sup>   | 60                   | Benzene   | А                              |  |  |  |  |  |
| Elongation at break %  | 140                  | Mineral oils  | А                              |  |  |  |  |  |
| Tensile modulus MN/m <sup>2</sup>  | 1500                 | Vegetable oils  | A                              |  |  |  |  |  |
| Notched impact strength kJ/m <sup>2</sup>  | 17                   | Weak alkalis  | А                              |  |  |  |  |  |
| Ball indentation MN/m <sup>2</sup>   | 100                  | Strong alkalis  | В                              |  |  |  |  |  |
| Application temperature max °C   | 120                  | Weak acids  | В                              |  |  |  |  |  |
| Volume resistivity cm  | 10^15                | Strong acids  | С                              |  |  |  |  |  |
| Dissapation factor tan. 10 <sup>3</sup> Hz   | 0,15                 | A = good  |                                |  |  |  |  |  |
| Dielectric strength MV/m   | 30                   | <b>B</b> = doubtful   |                                |  |  |  |  |  |
| Flammability UL94 > 1,6 mm   | V2                   | C = poor  |                                |  |  |  |  |  |
| Coefficient of friction (on steel)   | 0,3                  |   |                                |  |  |  |  |  |
| All data are indicative  |                      |   |                                |  |  |  |  |  |

Technical informations are indicative and can be updated. Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

**GANDINI FASTENERS SRL** Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350