

TECHNICAL PLASTIC AND METAL PARTS

| | | | | | | | | Snip & | Sna 096 | p rive | ∍t |
|----------------|---------------------|-----------------|-----------------------|---------|-------|------|------|--------|------------|--------|----|
| Code | Description | Price euro/1000 | % Price Change 1 2 | Package | A | В | С | D | Е | Fι | gr |
| 096 2010 124 0 | 1 MP 96-20-10 ROSSO | 180,00 | + 60% - | 500 | 7-7.2 | 19.8 | 20.2 | 34.4 | 1.7 | F2 | |

| Colour | Colour num | ber | | | | | | | |
|---|------------------------------|--|-----------------------------------|--|--|--|--|--|--|
| red | 124 (XXX XXXX XXX XX) | | | | | | | | |
| Colour descriptionredMatchesred.Featured colours reserved. Due to the | | ably matches RAL colour 3020 s in colour may occur. | | | | | | | |
| Material | | Material nr | | | | | | | |
| Nylon - 6 PA - 6 | | 01 (XXX XXXX XXX XX) | 01 (XXX XXXX XXX XX) | | | | | | |
| General informations: A strong, tough and durable material. Iubricant properties ideal for slide bea Always has to acclimatize for a few da | rings. Takes in app | rox 3% moisture at room temperatum perature up to approx 120°C. Nylo | ure and is then at its strongest. | | | | | | |
| Features | | Chimical resistance | | | | | | | |
| feature | DIN | Resistance to | Valutation | | | | | | |
| Relative density gr/cm ³ | 1,14 | Petrol | А | | | | | | |
| Tensile strength MN/m ² | 55 | Benzene | A | | | | | | |
| Elongation at break % | 250 | Mineral oils | А | | | | | | |
| Tensile modulus MN/m ² | 950 | Vegetable oils | А | | | | | | |
| Notched impact strength kJ/m ² | 35 | Weak alkalis | A | | | | | | |
| Ball indentation MN/m ² | 82 | Strong alkalis | В | | | | | | |
| Application temperature max °C | 120 | Weak acids | В | | | | | | |
| Volume resistivity cm | 10^15 | Strong acids | С | | | | | | |
| Dissapation factor tan. 10 ³ Hz | 0,2 | A = good | | | | | | | |
| Dielectric strength MV/m | 35 | B = doubtful | | | | | | | |
| Flammability UL94 > 1,6 mm | V2 | C = poor | | | | | | | |
| Coefficient of friction (on steel) | 0,3 | | | | | | | | |
| All data are indicative | | | | | | | | | |

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350