

TECHNICAL PLASTIC AND METAL PARTS

Snip & Snap rivet 096

ĺ	Code	Description	Price euro/1000	% Price (Change	Package	Α	В	С	D	Е	F gr
				1	2							
	096 1310 002 01	MP 96-13-10 GRIGIO	166,00	+ 60%	-	500	7-7.2	12.4	12.8	20.5	1.7	F2

Colour number
grey 002 (XXX XXXX XXX XXX)

Colour description grey
Matches Grey. Matches: Reasonably matches RAL colour 7000.
Featured colours reserved. Due to the screen, differences in colour may occur.

Material		Material nr				
Nylon - 6 PA - 6		01 (XXX XXXX XXX XX)				
General informations: A strong, tough and durable material. Iubricant properties ideal for slide bea Always has to acclimatize for a few da	rings. Takes in app	prox 3% moisture at room temperatu	re and is then at its strongest.			
Features		Chimical resistance				
feature	DIN	Resistance to	Valutation			
Relative density gr/cm ³	1,14	Petrol	Α			
Tensile strength MN/m ²	55	Benzene	Α			
Elongation at break %	250	Mineral oils	Α			
Tensile modulus MN/m ²	950	Vegetable oils	Α			
Notched impact strength kJ/m ²	35	Weak alkalis	Α			
Ball indentation MN/m ²	82	Strong alkalis	В			
Application temperature max °C	120	Weak acids	В			
Volume resistivity cm	10^15	Strong acids	С			
Dissapation factor tan. 10 ³ Hz	0,2	A = good				
Dielectric strength MV/m	35	B = doubtful C = poor				
Flammability UL94 > 1,6 mm	V2					
Coefficient of friction (on steel)	0,3					
All data are indicative						

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.l. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts
machining

GANDINI PASTENERS SRE viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350