

TECHNICAL PLASTIC AND METAL PARTS

Snip & Snap rivet
096

| Code | Description | Price euro/1000 | % Price Change | Package | A | B | C | D | E | F | gr |
|-----------------|-------------------|-----------------|----------------|---------|-----|-----|------|------|------|-----|----|
| | | | 1 2 | | | | | | | | |
| 096 1355 124 01 | MP 96-13-55 ROSSO | 166,00 | + 60% | - | 500 | 5.5 | 12.4 | 12.8 | 20.5 | 1.7 | F1 |

| Colour | Colour number |
|--|--|
| red | 124 (XXX XXXX XXX XX) |
| Colour description | red |
| Matches | red. Matches: Reasonably matches RAL colour 3020 |
| Featured colours reserved. Due to the screen, differences in colour may occur. | |

| Material | Material nr | | |
|--|----------------------------|---|------------|
| Nylon - 6 PA - 6 | 01 (XXX XXXX XXX XX) | | |
| General informations: A strong, tough and durable material. Suitable for connecting elements and other technical components. Owing to self lubricant properties ideal for slide bearings. Takes in approx 3% moisture at room temperature and is then at its strongest. Always has to acclimatize for a few days. Operational temperature up to approx 120°C. Nylon is self extinguishing. | | | |
| Features | Chimical resistance | | |
| feature | DIN | Resistance to | Valutation |
| Relative density gr/cm ³ | 1,14 | Petrol | A |
| Tensile strength MN/m ² | 55 | Benzene | A |
| Elongation at break % | 250 | Mineral oils | A |
| Tensile modulus MN/m ² | 950 | Vegetable oils | A |
| Notched impact strength kJ/m ² | 35 | Weak alkalis | A |
| Ball indentation MN/m ² | 82 | Strong alkalis | B |
| Application temperature max °C | 120 | Weak acids | B |
| Volume resistivity cm | 10^15 | Strong acids | C |
| Dissapation factor tan. 10 ³ Hz | 0,2 | A = good B = doubtful C = poor | |
| Dielectric strength MV/m | 35 | | |
| Flammability UL94 > 1,6 mm | V2 | | |
| Coefficient of friction (on steel) | 0,3 | | |
| All data are indicative | | | |

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.l. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy
Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution
of fasteners, fixing elements
and mechanical parts
machining

GANDINI FASTENERS SRL
viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

Sales department
250@gandini.it
tel +39 02 241 047 250

Administration
350@gandini.it
tel +39 02 241 047 350