

TECHNICAL PLASTIC AND METAL PARTS

							Qui	ickfas 095	tener
Code	Description	Price euro/1000	% Price Change 1 2	Package	A	В	C D	E	F gr
095 0010 699 01	MP 95-10 NERO	190,00	+ 60% -	100	7.6	1.5	8 1.9	4.2	F1

Colour	Colour num	ber					
black	k 699 (XXX XXX XXX XXX XX)						
Colour description black Matches brillant Featured colours reserved. Due to the		easonably matches RAL colour9005 es in colour may occur.					
Material		Material nr					
Nylon - 6 PA - 6		01 (XXX XXXX XXX XX)					
A strong, tough and durable material. ubricant properties ideal for slide bea Always has to acclimatize for a few da -eatures	rings. Takes in app	prox 3% moisture at room temperatu	ire and is then at its strongest.				
eature	DIN	Resistance to	Valutation				
Relative density gr/cm ³	1,14	Petrol	A				
Fensile strength MN/m ²	55	Benzene	A				
Elongation at break %	250	Mineral oils	A				
Γensile modulus MN/m ²	950	Vegetable oils	A				
Notched impact strength kJ/m ²	35	Weak alkalis	A				
3all indentation MN/m ²	82	Strong alkalis	В				
Application temperature max °C	120	Weak acids	В				
/olume resistivity cm	10^15	Strong acids	С				
Dissapation factor tan. 10 ³ Hz	0,2	A = good					
•	35	B = doubtful					
Dielectric strength MV/m	00	•					
C C	V2	C = poor					
Dielectric strength MV/m Flammability UL94 > 1,6 mm Coefficient of friction (on steel)		C = poor					

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350