

**TECHNICAL PLASTIC AND METAL PARTS** 

							Driv	ve fa <b>09</b>		er
Code	Description	Price euro/1000	% Price Change 1 2	Package	A	В	С	D	EF	= gr
094 0130 603 01	MP 94-130 BIANCO	98,00	+ 60% -	250	6.2	3.1	5.5	1.6	34	

Colour	Colour num	ber				
white	603 (XXX)	03 (XXX XXXX <b>XXX</b> XX)				
Colour description wh Matches wh Featured colours reserved. Due to the	ite. Matches: Roug	ghly matches RAL colour 9003 es in colour may occur.				
Material		Material nr				
Nylon - 6 PA - 6		01 (XXX XXXX XXX <b>XX</b> )				
General informations: A strong, tough and durable material. ubricant properties ideal for slide bea Always has to acclimatize for a few da	rings. Takes in app	prox 3% moisture at room temperatu mperature up to approx 120°C. Nylo	ire and is then at its strongest.			
Features		Chimical resistance				
feature	DIN	Resistance to	Valutation			
Relative density gr/cm <sup>3</sup>	1,14	Petrol	А			
Tensile strength MN/m <sup>2</sup>	55	Benzene	A			
Elongation at break %	250	Mineral oils	А			
Tensile modulus MN/m <sup>2</sup>	950	Vegetable oils	A			
Notched impact strength kJ/m <sup>2</sup>	35	Weak alkalis	A			
Ball indentation MN/m <sup>2</sup>	82	Strong alkalis	В			
Application temperature max °C	120	Weak acids	В			
/olume resistivity cm	10^15	Strong acids	С			
Dissapation factor tan. 10 <sup>3</sup> Hz	0,2	A = good				
Dielectric strength MV/m	35	$\mathbf{B} = doubtful$				
Flammability UL94 > 1,6 mm	V2	<b>C</b> = poor				
Coefficient of friction (on steel)	0,3					
All data are indicative						

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

**GANDINI FASTENERS SRL** Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350