

TECHNICAL PLASTIC AND METAL PARTS

						Driv	ve fas 094	stener I	
Code	Description	Price euro/1000	% Price Change 1 2	Package	A B	C D	Е	Fg	r
094 0320 603 01	MP 94-320 BIANCO	114,00	+ 60% -	250	7.8 4.1	6 1.8	3.5	4.5	٦

Colour	Colour num	ber						
white	ite 603 (XXX XXX XXX XXX)							
		hly matches RAL colour 9003 s in colour may occur.						
Material		Material nr						
Nylon - 6 PA - 6		01 (XXX XXXX XXX XX)						
General informations: A strong, tough and durable material. lubricant properties ideal for slide bea Always has to acclimatize for a few d	arings. Takes in app	prox 3% moisture at room temperatum mperature up to approx 120°C. Nylo	ire and is then at its strongest.					
Features		Chimical resistance						
feature	DIN	Resistance to	Valutation					
Relative density gr/cm ³	1,14	Petrol	А					
Tensile strength MN/m ²	55	Benzene	А					
Elongation at break %	250	Mineral oils	А					
Tensile modulus MN/m ²	950	Vegetable oils	А					
Notched impact strength kJ/m ²	35	Weak alkalis	А					
Ball indentation MN/m ²	82	Strong alkalis	В					
Application temperature max °C	120	Weak acids	В					
Volume resistivity cm	10^15	Strong acids	С					
Dissapation factor tan. 10 ³ Hz	0,2	A = good						
Dielectric strength MV/m	35	B = doubtful						
Flammability UL94 > 1,6 mm	V2	C = poor						
Coefficient of friction (on steel)	0,3							
All data are indicative								

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350