

TECHNICAL PLASTIC AND METAL PARTS

									orive fa 0	asteno 94	эr
Code	Description	Price euro/1000		inge 2	J. J			C			gr
094 0320 699 01	MP 94-320 NERO	114,00	+ 60%	-	250	7.8	4.1	6 1.	8 3.5	5 4.5	

Colour	Colour num	per						
black								
Colour description black Matches brillant Featured colours reserved. Due to the		easonably matches RAL colour9005 s in colour may occur.						
Material		Material nr						
Jylon - 6 PA - 6 01 (XXX XXXX XXX XX)								
A strong, tough and durable material. lubricant properties ideal for slide bea Always has to acclimatize for a few da	rings. Takes in app	prox 3% moisture at room temperatum prox 3% moisture at room temperature up to approx 120°C. Nylo	ire and is then at its strongest.					
Features		Chimical resistance						
feature	DIN	Resistance to	Valutation					
Relative density gr/cm ³	1,14	Petrol	А					
Tensile strength MN/m ²	55	Benzene	A					
Elongation at break %	250	Mineral oils	A					
Tensile modulus MN/m ²	950	Vegetable oils	A					
Notched impact strength kJ/m ²	35	Weak alkalis	А					
Ball indentation MN/m ²	82	Strong alkalis	В					
Application temperature max °C	120	Weak acids	В					
Volume resistivity cm	10^15	Strong acids	С					
Dissapation factor tan. 10 ³ Hz	0,2	A = good						
Dielectric strength MV/m	35	B = doubtful						
Flammability UL94 > 1,6 mm	V2	C = poor						
Coefficient of friction (on steel)	0,3							
Coefficient of friction (on steel)	0,0							

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350