

## TECHNICAL PLASTIC AND METAL PARTS

Drive fastener **094** 

| C      | Code      | Description      | Price euro/1000 | % Price C | Change | Package | Α   | В   | С   | D   | Е   | F   | gr |
|--------|-----------|------------------|-----------------|-----------|--------|---------|-----|-----|-----|-----|-----|-----|----|
|        |           |                  |                 | 1         | 2      |         |     |     |     |     |     |     |    |
| 094 02 | 10 603 01 | MP 94-210 BIANCO | 181,00          | + 60%     | -      | 250     | 6.2 | 3.6 | 3.7 | 1.6 | 1.2 | 2.1 |    |

Colour number

white 603 (XXX XXXX XXX XXX)

Colour description white Matches white. Matches: Roughly matches RAL colour 9003
Featured colours reserved. Due to the screen, differences in colour may occur.

MaterialMaterial nrNylon - 6 PA - 601 (XXX XXXX XXX)

## General informations:

A strong, tough and durable material. Suitable for connecting elements and other technical components. Owing to self lubricant properties ideal for slide bearings. Takes in approx 3% moisture at room temperature and is then at its strongest. Always has to acclimatize for a few days. Operational temperature up to approx 120°C. Nylon is self extinguishing.

| Features                                   |       | Chimical resistance |            |  |  |  |
|--|-------|---------------------|------------|--|--|--|
| feature                                    | DIN   | Resistance to       | Valutation |  |  |  |
| Relative density gr/cm <sup>3</sup>        | 1,14  | Petrol              | Α          |  |  |  |
| Tensile strength MN/m <sup>2</sup>         | 55    | Benzene             | Α          |  |  |  |
| Elongation at break %                      | 250   | Mineral oils        | Α          |  |  |  |
| Tensile modulus MN/m <sup>2</sup>          | 950   | Vegetable oils      | Α          |  |  |  |
| Notched impact strength kJ/m <sup>2</sup>  | 35    | Weak alkalis        | Α          |  |  |  |
| Ball indentation MN/m <sup>2</sup>         | 82    | Strong alkalis      | В          |  |  |  |
| Application temperature max °C             | 120   | Weak acids          | В          |  |  |  |
| Volume resistivity cm                      | 10^15 | Strong acids        | С          |  |  |  |
| Dissapation factor tan. 10 <sup>3</sup> Hz | 0,2   | A = good            |            |  |  |  |
| Dielectric strength MV/m                   | 35    | <b>B</b> = doubtful |            |  |  |  |
| Flammability UL94 > 1,6 mm                 | V2    | C = poor            |            |  |  |  |
| Coefficient of friction (on steel)         | 0,3   |                     |            |  |  |  |
| All data are indicative                    |       |                     |            |  |  |  |

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

**GANDINI FASTENERS SRL** viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts
machining

GANDINI PASTENERS SRE viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

**GANDINI FASTENERS SRL** Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350