

**TECHNICAL PLASTIC AND METAL PARTS** 

							Driv	ve fas 094	stene 1	r
Code	Description	Price euro/1000	% Price Change 1 2	Package	ΑB	С	D	Е	F	gr
094 0430 603 01	MP 94-430 BIANCO	136,00	+ 60% -	250	9 5.1	6.5	2.2	3.5	4.5	

Colour	Colour num	ber							
white	603 (XXX XXXX <b>XXX</b> XX)								
		ghly matches RAL colour 9003 es in colour may occur.							
Material	laterial Material nr								
Nylon - 6 PA - 6	n - 6 PA - 6 01 (XXX XXXX XXX <b>XX</b> )								
<b>General informations:</b> A strong, tough and durable material. lubricant properties ideal for slide bea Always has to acclimatize for a few da	rings. Takes in app	prox 3% moisture at room temperatu	ire and is then at its strongest.						
Features		Chimical resistance							
feature	DIN	Resistance to	Valutation						
Relative density gr/cm <sup>3</sup>	1,14	Petrol	А						
Tensile strength MN/m <sup>2</sup>	55	Benzene	A						
Elongation at break %	250	Mineral oils	А						
Tensile modulus MN/m <sup>2</sup>	950	Vegetable oils	А						
Notched impact strength kJ/m <sup>2</sup>	35	Weak alkalis	А						
Ball indentation MN/m <sup>2</sup>	82	Strong alkalis	В						
Application temperature max °C	120	Weak acids	В						
Volume resistivity cm	10^15	Strong acids	С						
Dissapation factor tan. 10 <sup>3</sup> Hz	0,2	A = good							
Dielectric strength MV/m	35	B = doubtful							
Flammability UL94 > 1,6 mm	V2	<b>C</b> = poor							
Coefficient of friction (on steel)	0,3								

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

**GANDINI FASTENERS SRL** Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350