


## TECHNICAL PLASTIC AND METAL PARTS



Code	Description	Price euro/1000	% Price Change 1 2	e Package	Α	В	С	D	E	F gr
094 1240 699 01	MP 94-1240 NERO	144,00	+ 60% -	250	6.0	3.6	5.5	1.0	3.0	4.0

Colour number
black 699 (XXX XXXX XXX XXX)

Colour description black

Matches brillant black. Matches: Reasonably matches RAL colour9005

Featured colours reserved. Due to the screen, differences in colour may occur.

Material		Material nr		
Nylon - 6 PA - 6		01 (XXX XXXX XXX XXX)		
lubricant properties ideal for slide	e bearings. Takes in ap	ecting elements and other technical prox 3% moisture at room temperat emperature up to approx 120°C. Nyl	ure and is then at its strongest.	
Features		Chimical resistance		
feature	DIN	Resistance to	Valutation	
Dolotivo donoity arlam3	1 11	Dotrol	Λ.	

feature	DIN	Resistance to	Valutation
Relative density gr/cm <sup>3</sup>	1,14	Petrol	Α
Tensile strength MN/m <sup>2</sup>	55	Benzene	Α
Elongation at break %	250	Mineral oils	Α
Tensile modulus MN/m <sup>2</sup>	950	Vegetable oils	Α
Notched impact strength kJ/m <sup>2</sup>	35	Weak alkalis	Α
Ball indentation MN/m <sup>2</sup>	82	Strong alkalis	В
Application temperature max °C	120	Weak acids	В
Volume resistivity cm	10^15	Strong acids	С
Dissapation factor tan. 10 <sup>3</sup> Hz	0,2	A = good	
Dielectric strength MV/m	35	<b>B</b> = doubtful	
Flammability UL94 > 1,6 mm	V2	C = poor	
Coefficient of friction (on steel)	0,3		
All data are indicative			

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.l. All rights reserved. No part of this web site may be reproduced in any form without express permission.

**GANDINI FASTENERS SRL** viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts
machining

GANDINI PASTENERS SRE viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

**GANDINI FASTENERS SRL** Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350