

## TECHNICAL PLASTIC AND METAL PARTS

Tube plug **045** 

| ı | Code            | Description   | Price euro/1000 | % Price 0 | Change | Package | Α  | В  | C D  | E F gr |
|---|-----------------|---------------|-----------------|-----------|--------|---------|----|----|------|--------|
| ı |                 |               |                 | 1         | 2      |         |    |    |      |        |
| ĺ | 045 1400 220 03 | MP 45-14 NERO | 216,00          | + 60%     | -      | 500     | 14 | 17 | 10 3 | F1     |

Colour Colour number

black 220 (XXX XXXX XXX XXX)

Colour description black
Matches black. Matches : Roughly matches RAL colour 9004
Featured colours reserved. Due to the screen, differences in colour may occur.

MaterialMaterial nrpolyethylene Ld - PE03 (XXX XXXX XXX)

## **General informations:**

Low pressure polyethylene is resistant to most chemicals. Therefore especially suitable for coverplugs and caps. Because of great flexibilty it is almost unbreakable. Does not take in moisture. Therefore insulating very well electrically. Polyethylene can not be glued and burns on after lighting it.

| Today not be glaca and barne on alter in   | griding it. |                          |            |  |  |  |  |
|--|-------------|--------------------------|------------|--|--|--|--|
| Features                                   |             | Chimical resistance      |            |  |  |  |  |
| feature                                    | DIN         | Resistance to            | Valutation |  |  |  |  |
| Relative density gr/cm <sup>3</sup>        | 0,92        | Petrol                   | Α          |  |  |  |  |
| Tensile strength MN/m <sup>2</sup>         | 10          | Benzene                  | Α          |  |  |  |  |
| Elongation at break %                      | 300         | Mineral oils             | Α          |  |  |  |  |
| Tensile modulus MN/m <sup>2</sup>          | 180         | Vegetable oils           | Α          |  |  |  |  |
| Notched impact strength kJ/m <sup>2</sup>  | -           | Weak alkalis             | Α          |  |  |  |  |
| Ball indentation MN/m <sup>2</sup>         | 14          | Strong alkalis           | Α          |  |  |  |  |
| Application temperature max °C             | 70          | Weak acids               | Α          |  |  |  |  |
| Volume resistivity cm                      | 10^17       | Strong acids             | В          |  |  |  |  |
| Dissapation factor tan. 10 <sup>3</sup> Hz | 0,0003      | A = good                 | A = good   |  |  |  |  |
| Dielectric strength MV/m                   | 60          | B = doubtful<br>C = poor |            |  |  |  |  |
| Flammability UL94 > 1,6 mm                 | -           |                          |            |  |  |  |  |
| Coefficient of friction (on steel)         | 0,17-1,5    |                          |            |  |  |  |  |
| All data are indicative                    |             |                          |            |  |  |  |  |

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.l. All rights reserved. No part of this web site may be reproduced in any form without express permission.

**GANDINI FASTENERS SRL** viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts
machining

GANDINI PASTENERS SRE viale Pier Paolo Pasolini, 83
Sesto San Giovanni Mi - Italy

**GANDINI FASTENERS SRL** Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350