

TECHNICAL PLASTIC AND METAL PARTS

1									apercli 044	þ
	Code	Description	Price euro/1000	% Price Change 1 2	Package	A	В	С	DE	F gr
	044 0004 113 32	MP 44- 4 BIANCO	184,00	+ 60% -	25	95	22	80	F	3

Colour	Colour numb	er							
vhite 113 (XXX XXXX XXX XXX)									
Colour description wh Matches wh Featured colours reserved. Due to the	ite. Matches: Rough	nly matches RAL colour 9003 s in colour may occur.							
Material		Material nr							
Polystyrene PS		32 (XXX XXXX XXX XX)	32 (XXX XXXX XXX XX)						
General informations: Impact-resistant Polystyreen is tough taken in. Is often being applied to amo Features			erial, because no moisture is						
feature	DIN	Resistance to	Valutation						
Relative density gr/cm ³	1,04	Petrol	В						
Tensile strength MN/m ²	50	Benzene	С						
Elongation at break %	2	Mineral oils	В						
Tensile modulus MN/m ²	3200	Vegetable oils	A						
Notched impact strength kJ/m ²	10	Weak alkalis	A						
Ball indentation MN/m ²	100	Strong alkalis	А						
Application temperature max °C	88	Weak acids	А						
Volume resistivity cm	10^16	Strong acids	А						
Dissapation factor tan. 10 ³ Hz	0,0004	A = good							
Dielectric strength MV/m	>40	B = doubtful	B = doubtful						
Flammability UL94 > 1,6 mm	HB	C = poor							
Coefficient of friction (on steel)	0,5								
All data are indicative									

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements viale Pier Paolo Pasolini, 83 and mechanical parts machining

GANDINI FASTENERS SRL Sesto San Giovanni Mi - Italy

Sales department 250@gandini.it tel +39 02 241 047 250 Administration 350@gandini.it tel +39 02 241 047 350