


## TECHNICAL PLASTIC AND METAL PARTS



Colour	Colour num	ber	
black	599 (XXX)	XXXX <b>XXX</b> XX)	
Colour descriptionblackMatchesjet blackFeatured colours reserved. Due to the	ack. Matches: Reas	onably matches RAL colour 9005 es in colour may occur.	
Material	Material nr		
Nylon - 6 PA - 6	01 (XXX XXXX XXX <b>XX</b> )		
General informations: A strong, tough and durable material. Iubricant properties ideal for slide bea Always has to acclimatize for a few da	arings. Takes in app	prox 3% moisture at room temperatum mperature up to approx 120°C. Nylo	and is then at its strongest.
Features		Chimical resistance	
feature	DIN	Resistance to	Valutation
Relative density gr/cm <sup>3</sup>	1,14	Petrol	А
Tensile strength MN/m <sup>2</sup>	55	Benzene	А
Elongation at break %	250	Mineral oils	А
Tensile modulus MN/m <sup>2</sup>	950	Vegetable oils	А
Notched impact strength kJ/m <sup>2</sup>	35	Weak alkalis	А
Ball indentation MN/m <sup>2</sup>	82	Strong alkalis	В
Application temperature max °C	120	Weak acids	В
	10^15	Strong acids	С
Volume resistivity cm	10 15	<b>5</b>	
•	0,2	A = good	
Dissapation factor tan. 10 <sup>3</sup> Hz		A = good B = doubtful	
Dissapation factor tan. 10 <sup>3</sup> Hz Dielectric strength MV/m	0,2	A = good	
Volume resistivity cm Dissapation factor tan. 10 <sup>3</sup> Hz Dielectric strength MV/m Flammability UL94 > 1,6 mm Coefficient of friction (on steel)	0,2 35	A = good B = doubtful	

Technical informations are indicative and can be updated.

Copyright Gandini Fasteners S.r.I. All rights reserved. No part of this web site may be reproduced in any form without express permission.

GANDINI FASTENERS SRL viale Pier Paolo Pasolini, 83 - 20099 Sesto S.Giovanni Milano Italy Tel. +39 02 241 047 250 Fax +39 02 241 047 74

Production and distribution of fasteners, fixing elements and mechanical parts machining

**GANDINI FASTENERS SRL** Sesto San Giovanni Mi - Italy **Sales department** 250@gandini.it tel +39 02 241 047 250

Administration 350@gandini.it tel +39 02 241 047 350